



4102

Product code: ArAlloy 4102

ArAlloy 4102 is HD polyethylene recommend film thickness at 10-25 micron with high tensile strength, good dart impact strength, good impact resistance and processability.

Application: blown film

Color: natural

Physical Properties	Value	Unit	Test method
Density	0.951	g/cm ³	ISO 1183
Melt point	135	°C	DSC
Melt Flow Rate (190 °C, 21.6 kg)	13-14	g/10min	ISO 1133
Oxidation Induction Time (210 °C, 20 °C/min)	90	min	ASTM D3895
Ash content	0	%	ISO 3451

Mechanical Properties	Value	Unit	Test method
Tensile Strength @ break	260	MPa	ISO 527
Elongation @ break	550	%	ISO 527
Flexural Modulus	450	MPa	ISO 178
Notched Izod Impact	N.B	kJ/m ²	ISO 180

Storage

Storage conditions should be in a cool and dry place.

- All above-mentioned data are typical values and not to be construed as real specifications. Users should confirm results by their own tests.